



B2

POLY BOND PVA PURE

PVA BONDING AGENT FOR CEMENT MIXES AND CONCRETE REPAIRS

BOND CEMENT MIX CONCRETE REPAIRS

POLY BOND PVA PURE is a single component PVA based, white viscous liquid, specially formulated for use as a multi-purpose adhesive and a bonding agent for cement mixes and as an admixture for mortars.

APPLICATION

POLY BOND PVA is ideally designed for use as multi-purpose adhesive in cement base mixes and as primer and integral bonding agent for concrete. Ideal for priming surfaces prior to plastering or painting. Use as an admixture in cement/sand and granolithic screeds.

ADVANTAGES

- Single component, easy to use.
- High bond strength provides excellent adhesion when used as bonding agent for cement based mixes.
- No chloride admixtures.
- Improves renders and mortars durability. Color go to clear when dries.
- Concentrated which make it economical.

COVERAGE

Bonding agent: 16m² when diluted 1 to 1 Sealer coat: 25m² when diluted 1 to 4
 Admixture: 20-25 L/100Kg Cement depending on use.

CLEANING

All tools should be cleaned immediately after finish- ing with water. Hardened materials may be cleaned mechanically.

PACKAGING

POLY BOND PVA is available in 20 Kg and 200Kg drums.

STORAGE

POLY BOND PVA shelf life is 12 months if stored at temperature between 5 °C and 50 °C. If these conditions are exceeded, POLYWED technical department should be contacted for advice.

TECHNICAL PROPERTIES

Appearance:	White viscous liquid
PH:	4-5
Specific gravity@25 °C:	1.0-1.05
Stability:	Stable in alkaline conditions
Compatibility:	Compatible with all types of Portland cement

CAUTION

Health and Safety:

POLY BOND PVA is non-toxic. Avoid skin and eye contact. Rubber gloves and eye protection should be worn all the time. The use of barrier cream is recommended on exposed areas of the skin.

Fire:

POLY BOND PVA is non flammable.

FOR MORE INFORMATION, PLEASE CONTACT PHONE NO. 00966 2 6204224

B2

POLY BOND PVA PURE

PVA BONDING AGENT FOR CEMENT MIXES AND CONCRETE REPAIRS

METHOD OF USE

Substrate preparation:

Where POLY BOND PVA should be used, the substrate should be sound, clean and free contamination. Surface laitance should be removed by light scrubbing or grit blasting.

Application:

General purpose bonding agent Strong adhesive form any substrates such as bricks, carpets, stone, tiles and wood may types. Apply a thin film of POLY BOND PVA over the prepared sides to be adhered together, allow coming thick and tacky, then press parts to each other and allow curing for approximately one day.

Cement screeds and plasters bonding agent:

Porous surfaces should be sealed using diluted POLY BOND PVA (1 part POLY BOND PVA to 4 parts water) which should be brushed vigorously into the prepared surfaces making sure to fill all pores and voids and allow it to get dry. Apply Diluted POLY- BOND PVA(1 part POLY BOND PVA to 1 part water) to the sealed surface using a brush. Make sure to apply the plaster or repair mortar whilst the applied coating is still tacky.

Sealer coat and dust proofing:

Diluted POLY BOND PVA(1 part POLY BOND PVA to 4 parts water) should be applied by brush over the target surface and allowed to dry. Note: for porous surfaces other coat should be applied to assure appropriate seal.

Admixture in cement/ sand screeds:

Use it as an admixture in cement/ sand screeds in both light traffic and heavy traffic areas. Supposed mixes is as the following:

COMPONENT	LIGHT TRAFFIC	HIGH TRAFFIC
Cement	100	100
Sand	300	100
Granite(4-6mm)	-	200
POLY BOND PVA	20	25

Prime the prepared surface with diluted POLY BOND PVA(1 part POLY BOND PVA to 4 parts water). The dry components should be mixed together. Add water to the mix to achieve a semi dry mix and then add the POLY BOND PVA and mix, more water could be added to achieve the required workability. Lay the mix on the tacky primed surface, tamp it and smooth it using trowels.



LEGAL DISCLAIMER: Polywed endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Polywed has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of the Technical Data sheets are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated of the technical Data Sheets.