



E7

ANCHOR FIX

High Performance, Three component epoxy adhesive anchor system

EPOXY ANCHOR FIX ADHESIVE

Adhesive anchor system has been specially formulated as a high performance, three epoxy component adhesive anchor system for threaded rods and reinforcing bars in uncracked concrete to suit transport applications.

ADVANTAGES

- Fast curing
- Standard guns can be used
- Can be used at low temperatures High load capacity
- Non-sag, even overhead Low wastage

USAGE

- As a fast curing anchoring adhesive for all grades of: Rebars / reinforcing steel
- Threaded rods
- Bolts and special fastening systems Concrete
- Hollow and solid masonry

PRECAUTION

Health and Safety

Is non-hazardous. However, it should not be swallowed or allowed to come into contact with skin or eyes. Suitable protective goggles should be worn. Splashes on the skin should be removed with water. In the case of contact with eyes, rinse immediately with plenty of water and seek medical advice. If swallowed, seek medical attention immediately. Do not induce vomiting.

PACKAGING

1 and 5 KG set

INSTRUCTION OF USE

- Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size.
- The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole.
- The drill hole must be thoroughly cleaned with the special steel brush.
- The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole.
- Mixing Part A + part B + part C Inject the adhesive into the hole.
- Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole.
- During the resin hardening time the anchor must not be moved or loaded

TECHNICAL PROPERTIES

Color	Sandy Beige
Density @25°C,kg/ltr	1.76±0.02
Pot lifemin@25°C	35±5
Adhesion to concrete (concretefailure)N/mm ²	>1.5
Tensile Strength N/mm ² @7days	15±0.5
Flexural Strength N/mm ² @7days	24±0.5
Compressive strength, N/mm ² @7days	75±1
Slant Shear strength, N/mm ² @7days	25±5

E7

POLYWED ANCHOR FIX

High Performance, Three component epoxy adhesive anchor system

HOLE DEPTH FACTORS

Hole depth depends on more than one factor:

- Concrete compressive strength
- Steel rebar grade (tensile strength) Ultimate design axial load
Concrete section depth
- Steel rebar diameter
- Each factor of the mentioned above is affecting the hole depth in different way. The concrete compressive strength is reversely affecting the hole depth i.e. the higher the compressive strength, the less the required hole depth for the same ultimate axial load, etc.
- For critical structural usage of POLYWED ANCHOR, we recommend going through pull off test to settle the right anchoring depth.

ANCHORING PARAMETERS

Hole diameter is all the time related to the embedded steel rebar diameter. The following table shows that relation which shows obviously the bigger the rebar diameter, the bigger the excess of the hole diameter, and that to give more tolerance for steel notches to be inserted easily.

Rebar diameter (mm)	Hole diameter (mm)
from 6 - 16	Rebar diameter + 4
from 18 - 32	Rebar diameter + 6
over 32	Rebar diameter + 8



LEGAL DISCLAIMER: Polywed endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Polywed has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of the Technical Data sheets are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated of the technical Data Sheets.