



P1

POLYWED EMULSION

Emulsion matte paint with a high quality for internal use.

MATT PAINT **INTERNAL**

Emulsion matte paint with a high quality for internal use consisting of acrylic copolymer and other chemicals to gain durability and resistance to weather and gives excellent properties for the application, and in conformity with the standards and specifications Arabia No. 2002/470.

APPLICATION

This is recommended as a class final for walls and ceilings, panels, gypsum and concrete surfaces for external use.

APPLICATION INSTRUCTIONS

- surface preparation and the preparation of a good
- clean it properly.
- Remove the old paint (if any) completely out of the surface, and to make sure that the surface completely clean and free of dirt, dust, oils and dirt.
- A single layer of the base coating and leave it to dry .
- Two Coat recommended from Ext. Emulsion.

APPLICATION TOOLS

- Roller
- Brush: Basic

PACKAGE

Pail 20 kg & 1 Gallon

VALIDITY OF THE PRODUCT STORAGE

Almost 12 months in a closed container - suitable cool, dry and ventilated place

TECHNICAL DATA

Density	1.5 at a temperature ° 25 m. ASTM D-14
Viscosity	105 Unit Corps at a temperature° 25 m. .ASTM D-562
Solid content	40% by volume .ASTM D-5201
Coverage rate	3 m ² / Kg, at a dry layer thickness of 40 microns without dilution.
Water resistance	Passing 7 days, .ASTM D-870
Alkali resistance	Passing 7 days) solution concentration%1ASTM D-1308
Resistance salts	Passing 7days) solution concentration% 1.5 (. .ASTM D- 1308
Adhesion strength	pass, .ASTM D-3359
Dryness time	Surface dry 30 minutes. Two hours to complete dryness.
Time interval between two layers coating	Minimum 4 hours.
Diluted	water
Dilution ratio	10- 15% (by volume, when using a roller and brush. And it depends on the weather conditions when in use

P1

POLYWED EMULSION

Emulsion matte paint with a high quality for internal use.

SPECIAL INSTRUCTIONS

- You must paint mixing well until it becomes homogeneous before use.
- Dilution appropriate quantity using a water to get the proper viscosity.
- Do not paint over wet surfaces only after fully dry drier.
- Not apply the next layer coating unless the previous layer to dry completely.
- Desired temperature 25-40 ° C, at least.
- Surface must be free of moisture and not less than 8% and moisture content of not more than 70%

SAFETY INSTRUCTIONS

- Ensure adequate ventilation during application, avoid inhaling mist or vapors during paint.
- Paint must be out of the reach of children.
- In case of contact with the paint to the skin or eyes should be washed thoroughly with water and should avoid eating, drinking or smoking during paint



LEGAL DISCLAIMER: Polywed endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Polywed has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of the Technical Data sheets are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated of the technical Data Sheets.