



T3

TILE ADHESIVE GB 770

TILE ADHESIVE FOR CERAMIC TILES USED FOR FLOORS AND WALLS

ADHESIVE

An improved tile adhesive that works in various environmental conditions and bonds all types of ceramic and natural stone tiles. Areas for use: Suitable for dry & wet conditions. Suitable for ceramic tiles and marble. In residential and commercial buildings.

APPLICATION

- For permanent fixing of all types of ceramic tiles.
- Can be used internally and externally.

ADVANTAGES

- Suitable for all types of ceramic .
- Ready for use, just requires the addition of water.
- High bond strength.
- Suitable for internal and external application.

STANDARDS

- TILE ADHESIVE SUPER GP 770 complies with BS 5980:1980 Class AA,Type 1 and ANSIA.118.1
- TILE ADHESIVE SUPER GP 770 complies with BS EN12004:2001,Type C1 for tensile adhesion strength.

CAUTIONS

Health and Safety:

As contains Portland cement, may cause irritation to skin or eyes. In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice if necessary.

TYPICAL PROPERTIES

Color:	white
Mix density:	1.8±0.1
Open time: 3mm thickness @ 25 °C	6 -10 min
Comp. Strength	> 10 KN
Max. application Temperature:	60 C
Tensile adhesion strength: (EN 1348:1999)	>0.50

YIELD

Approximately 5-6 m²/20 kg bag at 5 mm thick- ness.

CLEANING

TILE ADHESIVE SUPER GP 770 is available in 20 kg bags.

PACKAGING

Is available in 20 kg bags.

STORAGE

Shelf life is 12 months if stored at temperatures between 2 °C and 50 °C.

If these conditions are exceeded in any respect, technical department should be contacted for advice.

T3

TILE ADHESIVE GB 770

TILE ADHESIVE FOR CERAMIC TILES USED FOR FLOORS AND WALLS

METHOD OF USE

Substrate preparation:

All surfaces must be clean and free from oil, Grease or loose materials.
Substrate should be dimensionally stable. Allow time for shrinkage and structural strain movements.

Priming

TILE ADHESIVE SUPER GP 770 can be applied directly on concrete, cement plaster, screed and cement or lime mortar.

Mixing:

Spread to a uniform thickness of up to 5 mm. Place tiles firmly over the applied area. Do not apply large areas of adhesives that can not be covered within the open wet time of the adhesive.

Joints:

Tiles should not be placed over expansion or contraction joints. Stop tiles on joint edges and fill joints with flexible sealant.



LEGAL DISCLAIMER: Polywed endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Polywed has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of the Technical Data sheets are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated of the technical Data Sheets.