

UB ROOFCOAT

روف كوت يو بي

ACRYLIC ELASTOMERIC WATERPROOFING COMPOUND

PLASTER

REPAIR

Roofcoat UB is a cold-applied, one-component waterborne liquid applied waterproofing membrane, highly elastic and UV resistant.

USES

- For roof waterproofing solutions in both new construction and refurbishment projects
- For roofs with many details and complex geometry when accessibility is limited
- For cost efficient life cycle extension of failing roofs
For reflective coating to enhance energy efficiency by reducing cooling costs

ADVANTAGES

- One-component - ready to use
- Cold applied - requires no heat or flame
- Seamless waterproofing membrane
- UV resistant and UV stable
- Highly elastic and crack-bridging
- Easily recoated when needed - no stripping required
- Economic – provides a cost efficient life cycle extension for failing roofs
- Low VOC emitting water-based coating
- Excellent adhesion on porous and non-porous substrates
- Highly elastic and crack-bridging
- Water vapour permeable - allows the substrate to breathe

PRODUCT INFORMATION

Composition	Acrylic Polymeric emulsion
Packaging	20 kg pail
Appearance / Colour	White paste
Shelf Life	12 months from date of production
Storage Conditions	Roofcoat must be stored in a dry place, off the ground and well covered.
Density	Fresh mortar density: ~1.35 kg/l (at +25 °C) (EN ISO 1-2811)

TECHNICAL PROPERTIES

Strength	Tensile 1.0 N/mm ² @28 days Elongation at break 100% @ 28 days
----------	--

APPLICATION INFORMATION

Consumption	Roofcoat W1 is applied in 2 or 3 coats Total consumption ≥ 0.9 - 1.4 kg/m ² (≥ 0.6 - 1.0 l/m ²) Dry film thickness ≥ 0.3 - 0.5 mm Layer Thickness Note: Do not apply more than 0.75 kg/m ² of RoofcoatW1 per coat for layers without reinforcement.
Over coating	4 hrs

UB ROOFCOAT

روف كوت يو بي



ACRYLIC ELASTOMERIC WATERPROOFING COMPOUND

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be sound, of sufficient strength, clean, dry and free of dirt, oil, grease and other contamination. Depending on the material the substrate must be primed or mechanically cleaned. Grinding may be necessary to level the surface.

Suitable substrates are such as: concrete, bituminous felts and coatings, metal, brickwork, asbestos cement, ceramic tiles, wooden substrates

MIXING

Prior to application, stir roofcoat ECO thoroughly for 1 minute in order to achieve a homogeneous mixture. Over mixing must be avoided to minimize air entrainment.

APPLICATION

Prior to the application of the roofcoat the priming coat if used must have been cured tack-free.

Roof Coating: Roofcoat UB is applied in two or three coats. Prior to the application of a 2nd coat the indicated waiting time in the table above shall be allowed.

1. Apply the first coat of approx. 0.75 kg/m² (for non-absorbing substrates) – 1.00 kg/m² (for absorbing substrates) of roofcoat on a length of approx. 1m.
 2. Apply a second coat of approx. 0.25 kg/m² - 0.5kg/m² coat right into the wet fleece to achieve the required film thickness. The entire application shall happen while the roofcoat is still liquid and in wet condition.
 3. Repeat step 1–3 until the roof area is waterproofed.
- After the two coats are dry, seal the roof area with one or more additional coats of roofcoat (≥ 0.5 kg/m² per coat).

HEALTH AND SAFETY INFORMATION

Users must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

CLEANING OF TOOLS

Clean all tools and application equipment with clean water immediately after use. Hardened / cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application.

STORAGE

Store in a cool dry place under shade.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.



LEGAL DISCLAIMER: Polywed endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Polywed has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of the Technical Data sheets are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated of the technical Data Sheets.